

COTTON

<p>Quality Specifications on Physical Inspection and HVI Mode</p>	<p>Goods should lie within the Tenderable Range according to defined quality specifications. Outlaying goods will not be accepted for delivery.</p> <p>Ginning Pattern: Roller Ginned Cotton. Saw Ginned Cotton will be accepted with discount.</p> <ol style="list-style-type: none"> 1) Basis Grade: Standardized grade as per HVI Middling 31-3, accepted up to 41-3 with premium/ discount 2) Staple 2.5% span length - 29 mm (+/- 2mm) with premium/discount. Below 27 mm reject and above 31 mm no premium. 3) Micronaire (MIC): 3.6 – 4.8 +/-0.1 with discount. Below 3.5 and above 4.9 reject. 4) Tensile Strength: 28 GPT Minimum, No premium or discount 5) Trash: 3.5% +/-1.5% with premium and discount. More than 5% reject. 6) Moisture: Up to 8.5%. Rejected above 8.5%.
--	---

Note: The above specifications are subject to change and may vary on contract month basis. Members and their respective constituents are advised to refer the respective applicable circulars issued by the Exchange from time to time.