

## IRON ORE

<b>Quality specifications</b>	62% Fe fines	
	Iron Content	Min 62%
	Moisture	Max 10%
	Silica (SiO <sub>2</sub> )	Max 6 %
	Alumina (Al <sub>2</sub> O <sub>3</sub> )	Max 5%
	Phosphorus	Max 0.125%
	Sulphur	Max 0.1%
	Size of Fines	
	0 to 10 mm	Min 90%
	Less than 150 micron	Max 40%

**Note:** *The above specifications are subject to change and may vary on contract month basis. Members and their respective constituents are advised to refer the respective applicable circulars issued by the Exchange from time to time.*